

Advancements in Polymer-Based Sensors and Actuators for Structural Health Monitoring in Aerospace: A Comprehensive Review of Emerging Trends

Mehak Jonjua*

Abstract

Structural health monitoring (SHM) has emerged as a critical aspect of aerospace engineering, aiming to ensure the safety and reliability of aircraft structures throughout their operational lifespan. In aerospace engineering, structural health monitoring is one of the most important aspects of aerospace engineering. It aims to ensure that aircraft structures are safe and reliable over their entire service life. Polymer-based actuators and sensors have attracted a lot of attention because of their lightweight, flexibility, and low cost. The study will look at the current state of the art, as well as the emerging trends in aerospace SHM with polymer-based actuators. We will look at different types of polymers, fabrication methods, sensing mechanisms and integration strategies. We will also look at the capabilities and limitations of these technologies. In addition, we will also look at how machine learning algorithms can be integrated with data analytics to enable real-time tracking and predictive maintenance of aircraft structures. The goal of this review is to provide an overview of the state of the art and future directions in aerospace SHM that will benefit researchers and practitioners.

Keywords: Structural health monitoring, aerospace, polymer-based sensors, polymer-based actuators, emerging trends, machine learning, predictive maintenance.

INTRODUCTION

The aerospace sector is known for its rigorous safety standards and the continuous monitoring and upkeep of aircraft structures to ensure they remain safe for passengers. Structural health monitoring (SHM) has become pivotal in aerospace engineering, focusing on real-time evaluation of structural integrity, early damage detection, and forecasting potential failures. Structural health monitoring (SHM) involves sensing, collecting, and analyzing data of a structure periodically to determine its conditions over times [7]. Traditional SHM methods often involve bulky and expensive equipment, which can increase the weight and complexity of aircraft, thereby affecting their efficiency and performance. Active ultrasonic SHM system typically makes use of multiple lead zirconate titanate (PZT) piezoelectric ultrasonic transducers for ultrasonic excitation and detection in the targeted structure [1]

*Author for Correspondence

Mehak Jonjua

Professor, Sharda School of Media, film & Entertainment, Sharda University, Greater Noida, India.

Received Date: May 08, 2024

Accepted Date: June 01, 2024

Published Date: July 18, 2024

Citation Mehak Jonjua. Advancements in Polymer-Based Sensors and Actuators for Structural Health Monitoring in Aerospace: A Comprehensive Review of Emerging Trends. Journal of Polymer & Composites. 2024; 12(Special Issue 4): S173–S193.

In recent times, there's been a surge in interest in developing lightweight, adaptable, and cost-efficient sensor and actuator technologies for SHM in aerospace. Polymer-based materials have emerged as promising candidates due to their inherent characteristics like flexibility, lightweight nature, and easy fabrication. These materials offer distinct advantages for aerospace SHM, such as better adaptability to intricate geometries, enhanced durability, and compatibility with the lightweight composite materials widely used in modern aircraft construction.

The significance of polymer-based sensors and actuators in aerospace SHM lies in their capacity to deliver precise and dependable data on the structural health of aircraft components in real-time. This enables proactive maintenance strategies, minimizing downtime and repair expenses. By integrating sophisticated sensing and actuation capabilities directly into aircraft structures, these technologies have the potential to transform the approach to monitoring and maintaining structural integrity over an aircraft's lifespan.

Moreover, the advancement of polymer-based SHM systems aligns with broader industry trends toward embracing smart and connected aircraft technologies, including the Internet of Things (IoT) and digital twins. Through leveraging progress in materials science, sensor technology, and data analytics, aerospace manufacturers and operators can elevate the safety, efficiency, and sustainability of air travel, thereby enhancing the passenger experience and mitigating the environmental footprint of aviation.

Objectives of the Review

Seeks to offer a thorough examination of recent breakthroughs and emerging patterns in polymer-based sensors and actuators for aerospace structural health monitoring (SHM). By amalgamating the latest research findings and industry advancements, this paper aims to shed light on the potential of polymer-based technologies in tackling the evolving demands and hurdles of SHM in aerospace, paving the path for safer, more dependable, and more efficient aircraft systems.

The primary aim of this review is to present an in-depth analysis of recent strides and emerging trajectories in polymer-based sensors and actuators for SHM in aerospace applications. To achieve this overarching objective, the review delineates specific aims as follows:

- To explore the array of polymer materials currently being used or under investigation for SHM in aerospace, encompassing conductive polymers, piezoelectric polymers, electroactive polymers, shape memory polymers, dielectric elastomers, and ionic polymers.
- To scrutinize the various fabrication techniques employed in crafting polymer-based sensors and actuators, encompassing additive manufacturing, microfabrication, deposition methods, and hybrid approaches, and to assess their applicability to aerospace SHM requisites.
- To investigate into the sensing mechanisms enabled by polymer-based sensors, covering strain sensing, temperature sensing, damage detection, and chemical sensing, and to assess their efficacy in identifying and tracking structural health issues in aircraft components.
- To pinpoint the primary challenges and constraints linked with the development and deployment of polymer-based sensors and actuators for aerospace SHM, including durability and reliability concerns, scalability and mass production challenges, standardization and certification prerequisites, and integration with next-generation aircraft platforms.
- To propose forthcoming research pathways and technological innovations aimed at surmounting the aforementioned challenges and propelling the field of polymer-based SHM in aerospace forward, with a focus on enhancing sensor performance, optimizing integration methods, and harnessing emerging technologies like flexible electronics, nanomaterials, and 3D printing.

By addressing these objectives, this review endeavors to equip researchers, engineers, and industry stakeholders with valuable insights into the present state-of-the-art and future prospects of polymer-based sensors and actuators for aerospace SHM, thereby facilitating the development of safer, more dependable, and more efficient aircraft systems.

POLYMER MATERIALS FOR STRUCTURAL HEALTH MONITORING (SHM)

Polymer materials have garnered significant attention in aerospace structural health monitoring (SHM) due to their unique characteristics, including lightweight properties, flexibility, and ease of fabrication. Various types of polymers are being explored and utilized for SHM, each offering specific advantages and functionalities. Below, we outline several key categories of polymer materials commonly employed in SHM:

- **Conductive Polymers:** Polymers like polyaniline, polypyrrole, and polythiophene exhibit electrical conductivity properties useful for sensing. They can detect changes in electrical resistance in response to mechanical strain, temperature variations, or chemical exposure, functioning as strain, temperature, or chemical sensors. Conductive polymers are often integrated into composite materials or applied as coatings on structural surfaces to enable distributed sensing for SHM.
- **Piezoelectric Polymers:** Examples include polyvinylidene fluoride (PVDF) and its copolymers, which generate electrical charges under mechanical deformation. They serve as both sensors and actuators, detecting structural vibrations, strain, and impact events, and inducing vibrations or deformations for structural health assessment or damage mitigation.
- **Electroactive Polymers (EAPs):** Dielectric elastomers, ionic polymers, and conducting polymer composites fall under this category. They deform significantly in response to electrical stimulation, making them suitable for actuation in SHM. EAP actuators enable adaptive structures with self-sensing and self-healing capabilities, enhancing structural performance and durability.
- **Shape Memory Polymers (SMPs):** These materials undergo reversible changes in shape or stiffness due to external stimuli like temperature or light. SMPs are utilized for damage detection, structural repair, and morphing applications in aerospace structures, offering benefits in weight savings and operational efficiency.
- **Other Polymer Composites:** Besides the mentioned categories, polymer composites and hybrid materials are being developed for SHM. These composites typically consist of polymer matrices reinforced with conductive fillers such as carbon nanotubes or graphene to impart sensing or actuation capabilities. Tailoring the composition and microstructure of these composites enhances sensitivity, durability, and multifunctionality for SHM.

Polymer materials hold immense potential for advancing aerospace SHM, facilitating the development of lightweight, multifunctional, and cost-effective sensor and actuator systems. Ongoing research and innovation in polymer science and engineering are expected to drive further SHM technology advancements, ultimately enhancing aircraft structure safety, reliability, and efficiency.

Polymers for Sensor Applications

Polymers play a crucial role in sensor applications for structural health monitoring (SHM) in aerospace due to their versatility, lightweight nature, and adjustable properties. Different types of polymers are engineered or chosen based on their specific sensing mechanisms and compatibility with aerospace environments. Here are descriptions of key polymer categories commonly used for sensor applications in aerospace SHM:

- *Conductive Polymers:* Polymers like polyaniline (PANI), polypyrrole (PPy), and poly(3,4-ethylenedioxythiophene) (PEDOT) possess intrinsic electrical conductivity that can be altered by external stimuli. Incorporated into sensor devices, they exhibit changes in electrical resistance in response to mechanical strain, temperature shifts, or exposure to certain chemicals, making them suitable for strain, temperature, humidity, and gas sensors in aerospace SHM. They are often applied onto flexible substrates or integrated into composite materials for distributed sensing across aircraft structures.
- *Piezoelectric Polymers:* Examples include polyvinylidene fluoride (PVDF), poly(vinylidene fluoride-trifluoroethylene) (PVDF-TrFE), and poly(vinylidene fluoride-chlorotrifluoroethylene) (PVDF-CTFE), which possess inherent piezoelectric properties, generating electric charge under mechanical deformation. Used in SHM sensors as film-based transducers or embedded within structural components, they detect strain, vibration, impact events, or acoustic emissions with high sensitivity, broad frequency response, and compatibility with flexible substrates, ideal for monitoring dynamic loads and structural integrity in aerospace.
- *Electroactive Polymers (EAPs):* This class includes materials like dielectric elastomers, conducting polymer composites, and ionic polymers, all undergoing significant deformation under electrical stimulation. Dielectric elastomers offer large strains and high actuation forces, suitable for applications requiring extensive deformations, such as morphing structures or soft robotics.

Conducting polymer composites combine polymer mechanical properties with carbon nanotubes or graphene's electrical conductivity for multifunctional sensors detecting strain, pressure, or damage. Ionic polymers, like Nafion, change volume in response to ion migration, serving as humidity sensors or actuators in SHM systems.

- *Optical Polymers*: This category includes polymeric optical fibers (POFs), polymer thin films, and polymer-based nanocomposites, offering advantages for sensing in aerospace SHM. POFs transmit light signals over long distances with minimal signal loss, suitable for distributed strain sensing or temperature monitoring in aircraft structures. Polymer thin films and nanocomposites exhibit optical property changes, like refractive index or luminescence, responding to mechanical strain, temperature shifts, or chemical exposure, enabling their use as optical sensors in SHM.

These key polymer categories are instrumental in sensor applications for aerospace SHM. Leveraging their unique properties and functionalities, researchers and engineers can develop innovative sensor technologies for accurate, reliable, and real-time monitoring of aircraft structures, enhancing safety, efficiency, and reliability in aerospace operations.

Conductive Polymers

Conductive polymers, a class of materials displaying electrical conductivity modifiable by external stimuli like mechanical strain, temperature variations, or exposure to specific chemicals, have gained considerable attention for sensor applications in aerospace structural health monitoring (SHM). Their lightweight, flexible nature and adjustable electrical properties make them appealing for such applications. Here, we explore the attributes and uses of conductive polymers in aerospace SHM:

- *Polyaniline (PANI)*: PANI stands out among conductive polymers due to its straightforward synthesis, environmental stability, and customizable conductivity via doping. Doped PANI finds application in aerospace SHM sensors for detecting mechanical strain, temperature changes, and chemical substances, promising benefits in monitoring structural integrity and environmental factors in aircraft components.
- *Polypyrrole (PPy)*: PPy, with its high conductivity, chemical stability, and biocompatibility, is extensively studied for sensor applications in aerospace SHM. PPy sensors detect strain, corrosion, and gases, facilitating early detection of structural damage or degradation and supporting proactive maintenance strategies.
- *Poly(3,4-ethylenedioxythiophene) (PEDOT)*: Known for its high conductivity, optical transparency, and mechanical flexibility, PEDOT lends itself to fabrication into thin films or coatings for transparent or flexible substrate applications like touch sensors or wearable electronics. In aerospace SHM, PEDOT-based sensors monitor structural strain, temperature fluctuations, and chemical exposure, offering advantages in weight, conformability, and integration ease.
- *Aerospace SHM Applications*: Conductive polymers serve varied purposes in aerospace SHM, from strain sensors within composite materials to surface-mounted sensors monitoring temperature fluctuations or detecting corrosive agents. Real-time data from these sensors enable early identification of issues like fatigue cracking, corrosion, or impact damage, supporting condition-based maintenance strategies and enhancing operational efficiency and safety.

Despite their promise, conductive polymer sensors encounter challenges concerning long-term stability, calibration, and environmental resilience in aerospace settings. Ongoing research addresses these challenges through material refinement, advanced fabrication methods, and integration with complementary sensor technologies. Exploration of multifunctional conductive polymer composites and hybrid sensor systems is gaining traction to boost sensing capabilities and reliability in aerospace SHM.

Conductive polymers offer substantial potential for advancing aerospace structural health monitoring by delivering lightweight, flexible, and cost-effective sensor solutions. Persistent research and development efforts in this domain are anticipated to yield advanced conductive polymer sensors, enhancing aircraft operation safety, efficiency, and reliability.

Piezoelectric Polymers

Piezoelectric polymers, capable of generating electric charge in response to mechanical deformation and vice versa, have garnered significant attention for sensor and actuator applications in aerospace structural health monitoring (SHM). Their high sensitivity, broad frequency response, and compatibility with flexible substrates make them particularly attractive. Here, we delve into the characteristics and applications of piezoelectric polymers in aerospace SHM:

- *Polyvinylidene Fluoride (PVDF)*: PVDF, renowned for its excellent piezoelectric properties, chemical stability, and mechanical flexibility, is widely utilized. PVDF-based sensors, fabricated as thin films, fibers, or coatings, detect mechanical strain, vibration, impact events, or acoustic emissions in aerospace structures. They offer benefits like high sensitivity, low power consumption, and resilience to harsh environmental conditions, ideal for long-term monitoring and damage detection.
- *PVDF Copolymers*: Copolymers like poly(vinylidene fluoride-trifluoroethylene) (PVDF-TrFE) and poly(vinylidene fluoride-chlorotrifluoroethylene) (PVDF-CTFE) exhibit enhanced piezoelectric properties compared to pure PVDF. Tailorable for specific performance characteristics, such as increased sensitivity or improved thermal stability, they're employed in aerospace SHM for monitoring, impact detection, and non-destructive testing in aircraft components, ensuring early damage or defect detection and operational safety.
- *Applications in Aerospace SHM*: Piezoelectric polymer sensors find wide-ranging applications in aerospace SHM, from monitoring composite materials to non-destructive testing of metallic structures. Integrated into aircraft components like wings, fuselages, and engine mounts, they monitor mechanical loads, detect fatigue cracks, or assess impact damage. Lightweight, conformable, and low-profile, they seamlessly integrate into complex geometries and harsh environments.

Despite their advantages, piezoelectric polymer sensors face challenges such as temperature sensitivity, cross-sensitivity to environmental factors, and signal processing complexity. Research focuses on addressing these issues through material optimization, sensor packaging, and advanced signal processing algorithms. Hybrid sensor systems, combining piezoelectric polymers with other modalities, are gaining traction to enhance overall performance and reliability in aerospace SHM.

Polymers offer significant potential for advancing aerospace structural health monitoring, providing highly sensitive, robust, and versatile sensor solutions. Ongoing research and innovation are expected to yield next-generation piezoelectric polymer sensors, enhancing aircraft structure safety, efficiency, and reliability.

Electroactive Polymers

Electroactive polymers (EAPs) belong to a class of materials capable of undergoing significant deformation or shape changes when subjected to electrical stimulation. This behavior, termed electroactivity, enables them to reversibly alter their shape, size, or mechanical properties under an electric field. EAPs have garnered substantial interest for both actuator and sensor applications in aerospace structural health monitoring (SHM) due to their lightweight nature, ability to deform extensively, and adaptability to complex geometries. Below, we explore the characteristics and applications of electroactive polymers in aerospace SHM:

- *Dielectric Elastomers*: These EAPs can undergo large deformations when exposed to an electric field. Typically comprising a compliant elastomer matrix between compliant electrodes, they deform under electrostatic forces, enabling actuation or sensing. Dielectric elastomer actuators have found use in morphing wing structures, active vibration control, and adaptive damping within aerospace systems.
- *Conducting Polymer Composites*: Combining polymer mechanical properties with electrical conductivity from fillers like carbon nanotubes, graphene, or metallic nanoparticles, these composites display electroactive behavior due to piezoresistive or electromechanical coupling

effects. They serve as sensors for detecting mechanical strain, pressure, or impact events in aerospace structures, offering high sensitivity, cost-efficiency, and ease of fabrication.

- *Ionic Polymers:* Ionic polymers, exemplified by Nafion, undergo volumetric changes via ion migration under an applied electric field. Combining traits of dielectric elastomers and conducting polymer composites, they suit actuation and sensing applications in aerospace SHM. Ionic polymer actuators have been studied for active vibration control, shape morphing, and adaptive optics in aerospace systems.
- *Applications in Aerospace SHM:* EAPs find diverse uses in aerospace SHM, from controlling surfaces to sensing structural deformations or damage. Integrated into aircraft components like wings, flaps, and rudders, they provide adaptive control, structural health monitoring, or damage detection. Offering lightweight design, low power consumption, and high efficiency, electroactive polymer actuators and sensors are ideal for aerospace applications where weight and energy efficiency are paramount.
- *Challenges and Future Directions:* Despite their promise, EAPs encounter challenges such as material degradation, electrical breakdown, and mechanical fatigue in aerospace conditions. Future research focuses on overcoming these obstacles through material refinement, encapsulation techniques, and system-level optimization. Moreover, hybrid actuator and sensor systems, combining EAPs with other modalities, aim to achieve multifunctionality and robustness in aerospace SHM applications.

Electroactive polymers hold significant promise for advancing aerospace structural health monitoring by providing lightweight, adaptable, and energy-efficient solutions for actuation and sensing. Ongoing research and innovation are expected to yield next-generation electroactive polymer systems, enhancing the safety, efficiency, and reliability of aircraft structures.

Polymers for Actuator Applications

Polymers play a pivotal role in actuator applications for structural health monitoring (SHM) in aerospace, facilitating the creation of adaptive structures, morphing wings, and active vibration control systems. Actuator polymers offer benefits like lightweight construction, flexibility, and significant deformation capabilities, making them ideal for aerospace applications prioritizing weight savings and efficiency. Here, we delineate three key categories of polymers utilized for actuator applications in aerospace SHM:

Shape Memory Polymers (SMPs)

SMPs are materials capable of reversible changes in shape or stiffness triggered by external stimuli like temperature, light, or electric fields. These polymers possess two distinct states: a temporary shape, subject to deformation or molding, and a permanent shape ingrained within the material. When prompted by the appropriate stimulus, SMPs can revert to their original shape or properties, making them well-suited for actuator applications in aerospace SHM. Here are their key characteristics and applications:

- *Reversible shape change:* SMPs can undergo substantial deformations and regain their initial shape upon external stimulus.
- *Tunable properties:* The shape memory effect in SMPs can be adjusted by modifying material composition, processing conditions, or stimulus parameters.
- *Biocompatibility:* Many SMP formulations exhibit biocompatibility, rendering them suitable for medical and aerospace applications necessitating interaction with biological tissues.

Applications:

- *Morphing wing structures:* SMP actuators integrate into aircraft wings, facilitating adaptive wing morphing for optimized aerodynamics and fuel efficiency.
- *Deployable structures:* SMP-based actuators enable deployment or retraction of components like antennas, solar panels, or landing gear in aerospace systems.

- *Active camouflage:* SMP materials can be engineered to alter color or pattern in response to external stimuli, offering active camouflage capabilities for military aircraft.

Dielectric Elastomers

Dielectric elastomers, a type of electroactive polymer, undergo significant deformation under an electric field. Comprising a compliant elastomer matrix sandwiched between compliant electrodes, they deform due to electrostatic forces upon exposure to an electric field, enabling actuation or sensing capabilities. Dielectric elastomers boast advantages such as high energy density, low power consumption, and rapid response times, making them suitable for aerospace actuator applications. Here are their key characteristics and applications:

- *Large deformation capabilities:* Dielectric elastomers achieve strains of up to several hundred percent, facilitating substantial actuation displacements.
- *Fast response times:* With actuation occurring within milliseconds, dielectric elastomers suit dynamic control applications.
- *High energy density:* These elastomers can store and release significant mechanical energy, enabling efficient actuation with minimal power consumption.

Applications:

- *Active vibration control:* Dielectric elastomer actuators integrate into aerospace structures to actively dampen vibrations and reduce structural fatigue.
- *Morphing wing structures:* Employed to induce shape changes in aircraft wings, dielectric elastomer actuators enable adaptive aerodynamics and improved flight performance.
- *Soft robotics:* Dielectric elastomers find use in soft robotic applications like grippers, manipulators, and locomotion systems due to their compliant and deformable nature.

Ionic Polymers

Ionic polymers, exemplified by Nafion, undergo volumetric changes upon ion migration under an applied electric field. Displaying traits of both dielectric elastomers and conducting polymer composites, they suit actuation and sensing applications in aerospace SHM. Ionic polymer actuators offer benefits like high mechanical compliance, low operating voltages, and environmental robustness, making them suitable for soft robotics and adaptive structures. Here are their key characteristics and applications:

- *High mechanical compliance:* Ionic polymers are highly flexible materials that deform under low applied voltages, enabling soft and flexible actuation.
- *Low operating voltages:* Ionic polymer actuators typically function at voltages on the order of volts, rendering them compatible with portable and low-power applications.
- *Environmental robustness:* Resistant to moisture, chemicals, and radiation, ionic polymers withstand harsh operating environments.

Applications:

- *Soft robotics:* Ionic polymer actuators drive soft robotic applications such as artificial muscles, grippers, and tentacles, thanks to their compliant and biomimetic behavior.
- *Microfluidics:* Employed to control fluid flow in microfluidic devices, ionic polymer actuators find applications in drug delivery, lab-on-a-chip systems, and biomedical diagnostics.
- *Biomimetic systems:* Utilized in biomimetic systems resembling the movement and behavior of biological organisms, ionic polymer actuators power devices like fish-like robots or insect-inspired drones for exploration and surveillance tasks.

Polymers play an essential role in actuator applications for structural health monitoring in aerospace, facilitating the development of adaptive structures, morphing wings, and active vibration control systems. Shape memory polymers, dielectric elastomers, and ionic polymers offer distinctive

advantages and capabilities for actuation in aerospace applications, contributing to enhanced performance, efficiency, and safety in aircraft systems.

FABRICATION TECHNIQUES

Fabrication techniques play a critical role in the development of polymer-based sensors and actuators for structural health monitoring (SHM) in aerospace applications. These techniques enable the precise fabrication of sensor components, integration into aircraft structures, and customization of sensor properties to meet specific performance requirements. Here, we describe several key fabrication techniques commonly employed in the production of polymer-based sensors and actuators for aerospace SHM:

Additive Manufacturing

Additive manufacturing, also known as 3D printing, is a versatile fabrication technique that allows for the layer-by-layer deposition of materials to create complex three-dimensional (3D) structures. Additive manufacturing offers several advantages for the fabrication of polymer-based sensors and actuators, including rapid prototyping, design flexibility, and customization capabilities. Here's how additive manufacturing is utilized in aerospace SHM:

- **Process:** Additive manufacturing begins with the creation of a digital 3D model of the desired sensor or actuator component using computer-aided design (CAD) software. The CAD model is sliced into thin horizontal layers, and each layer is sequentially deposited or cured to build up the final 3D structure. Various additive manufacturing techniques can be employed, including fused deposition modeling (FDM), stereolithography (SLA), selective laser sintering (SLS), and inkjet printing, depending on the material properties and desired resolution of the final part.
- **Applications:** Rapid prototyping: Additive manufacturing allows for the rapid fabrication of prototype sensor and actuator components, enabling iterative design improvements and validation of performance.
- **Complex geometries:** Additive manufacturing enables the creation of complex, intricate geometries that are difficult or impossible to achieve using traditional manufacturing methods, allowing for the integration of sensors and actuators into unconventional aircraft structures.
- **Customization:** Additive manufacturing enables the customization of sensor and actuator properties, such as material composition, shape, and size, to meet specific application requirements and performance objectives.

Microfabrication

Microfabrication is a fabrication technique used to create microscale structures and devices with high precision and resolution. Microfabrication techniques are particularly relevant for the production of miniaturized sensors and actuators for aerospace SHM, where size, weight, and power constraints are critical considerations. Here's how microfabrication is utilized in aerospace SHM:

- **Process:** Microfabrication techniques typically involve photolithography, etching, and deposition processes to pattern and shape thin films or substrates at the microscale. Photolithography is used to transfer a pattern onto a photosensitive substrate using UV light and a photomask, defining the features of the sensor or actuator. Etching processes, such as wet etching or dry etching, are employed to selectively remove material from the substrate to create the desired structures. Deposition techniques, such as physical vapor deposition (PVD) or chemical vapor deposition (CVD), are used to deposit thin films of materials onto the substrate to create sensor electrodes or actuator layers.
- **Applications:** It can be applied in the following cases-
 - **Miniaturization:** Microfabrication enables the production of miniaturized sensors and actuators with dimensions on the order of micrometers to millimeters, allowing for integration into compact aerospace systems and structures.
 - **High-resolution patterning:** Microfabrication offers high-resolution patterning capabilities, enabling the creation of intricate sensor arrays, microelectrodes, and microfluidic channels for

- advanced SHM applications.
- *Batch fabrication:* Microfabrication techniques can be scaled up for batch fabrication of sensor and actuator components, allowing for high-throughput production and cost-effective manufacturing of aerospace SHM systems.

Deposition Techniques

Deposition techniques involve the deposition of thin films or coatings onto substrates to create sensor electrodes, actuator layers, or protective coatings for aerospace SHM applications. These techniques offer precise control over film thickness, composition, and morphology, enabling the fabrication of functional sensor and actuator components with tailored properties. Here's how deposition techniques are utilized in aerospace SHM:

- **Process:** Deposition techniques can be classified into physical vapor deposition (PVD), chemical vapor deposition (CVD), and solution-based deposition methods, such as spin coating, dip coating, and spray coating. PVD techniques, such as sputtering or evaporation, involve the physical vaporization of a solid material followed by its condensation onto a substrate to form a thin film. CVD techniques involve the chemical reaction of gaseous precursors on the substrate surface to deposit a thin film of the desired material. Solution-based deposition methods involve the deposition of a solution or suspension of the material onto the substrate surface, followed by solvent evaporation or chemical curing to form a thin film.
- **Applications:** Thin-film sensors: Deposition techniques are used to fabricate thin-film sensors with precise control over film thickness, composition, and morphology, enabling the development of high-performance sensors for aerospace SHM applications.
- **Electrode fabrication:** Deposition techniques are employed to create conductive electrode layers for sensor devices, enabling the integration of sensors into aircraft structures and components.
- **Protective coatings:** Deposition techniques can be used to apply protective coatings onto sensor and actuator components to enhance their durability, corrosion resistance, and environmental stability in aerospace environments.

Hybrid Approaches

Hybrid approaches involve the combination of multiple fabrication techniques to achieve the desired properties and functionalities of sensor and actuator components for aerospace SHM applications. Hybrid approaches leverage the strengths of different fabrication techniques to overcome the limitations of individual methods and enable the production of advanced sensor and actuator systems. Here's how hybrid approaches are utilized in aerospace SHM:

- **Integration of additive manufacturing with microfabrication:** Additive manufacturing techniques can be combined with microfabrication processes to create complex 3D structures with embedded microscale features, enabling the fabrication of integrated sensor and actuator systems for aerospace SHM.
- **Combination of deposition techniques with lithography:** Deposition techniques, such as PVD or CVD, can be combined with photolithography to create patterned thin films or microelectrodes on substrates, enabling the fabrication of miniaturized sensor arrays or microactuator arrays for aerospace SHM. The fabrication techniques play a crucial role in the development of polymer-based sensors and actuators for aerospace SHM, enabling the precise fabrication of sensor components, integration into aircraft structures, and customization of sensor properties to meet specific performance requirements. Additive manufacturing, microfabrication, deposition techniques, and hybrid approaches offer versatile and scalable fabrication solutions for aerospace SHM applications, driving advancements in sensor technology and enabling safer, more reliable aircraft systems.

SENSING MECHANISMS

Sensing mechanisms are pivotal for polymer-based sensors in aerospace structural health monitoring (SHM), allowing the detection and quantification of various physical and chemical parameters critical

for aircraft structure assessment. These mechanisms offer insights into the condition of aircraft structures and components. Here, we delineate several key sensing mechanisms employed in polymer-based sensors for aerospace SHM.

Strain Sensing

Strain sensing involves measuring mechanical deformation or elongation experienced by a material under applied loads. In aerospace SHM, strain sensors are vital for monitoring structural integrity, fatigue crack detection, and load distribution assessment across aircraft components. Polymer-based strain sensors exploit piezoresistive, piezoelectric, or capacitive properties to detect changes in electrical resistance, voltage, or capacitance due to mechanical strain. Below are the strain sensing mechanisms in polymer-based sensors:

- **Piezoresistive strain sensing:** Conductive polymers, like polyaniline or carbon nanotube composites, undergo changes in electrical resistance with mechanical strain. Deformation of the polymer alters the spacing between conductive particles, resulting in resistance variations correlated with applied strain.
- **Piezoelectric strain sensing:** Piezoelectric polymers, such as polyvinylidene fluoride (PVDF), produce electric charge with mechanical deformation. Strain-induced polymer deformation causes polarization and voltage output changes, enabling strain measurement.
- **Capacitive strain sensing:** These sensors utilize changes in capacitance from deformation of a polymer-based dielectric material between two electrodes. Variations in electrode distance due to applied strain lead to proportional capacitance changes, facilitating strain measurement.

Applications include structural health monitoring and load monitoring, aiding in monitoring mechanical loads, fatigue crack detection, and structural integrity assessment during flight operations.

Temperature Sensing

Temperature sensing involves measuring thermal energy or temperature variations within an environment or material. In aerospace SHM, temperature sensors are crucial for monitoring thermal gradients, overheating detection, and ensuring proper aircraft system operation. Polymer-based temperature sensors exploit thermal expansion, electrical conductivity, or optical properties to detect temperature changes. Below are the temperature sensing mechanisms in polymer-based sensors:

- **Thermal expansion sensing:** Thermally responsive polymers, such as shape memory polymers or elastomers, undergo dimensional changes with temperature variations. These changes are measured using strain-sensitive techniques or displacement sensors to infer temperature changes.
- **Conductive temperature sensing:** Conductive polymers, such as carbon black-filled polymers or metal nanoparticle composites, experience changes in electrical conductivity with temperature variations. Changes in resistance or voltage output allow accurate temperature detection.
- **Optical temperature sensing:** Polymer-based optical fibers or thin films exhibit changes in optical properties, like refractive index or luminescence, with temperature changes. Optical sensors use alterations in light transmission, absorption, or emission to measure temperature changes within aircraft components.

Applications include engine monitoring and avionics cooling, facilitating efficient engine performance monitoring and preventing overheating, as well as maintaining proper cooling and thermal management in avionics compartments and cabin environments.

Damage Detection

Damage detection involves identifying and characterizing defects, cracks, or material degradation within aircraft structures or components. In aerospace SHM, damage sensors are crucial for early detection of structural anomalies, preventing catastrophic failures, and minimizing maintenance downtime. Polymer-based damage sensors utilize changes in mechanical, electrical, or optical properties to detect damage presence or progression. Below are the damage detection mechanisms in polymer-based sensors:

- *Crack detection:* Conductive polymer-based sensors detect crack formation or propagation within aircraft structures by monitoring changes in electrical resistance or voltage output at crack locations.
- *Delamination detection:* Capacitive or impedance-based sensors detect delamination or debonding between composite layers by monitoring changes in capacitance or impedance resulting from layer separation.
- *Chemical sensing:* Polymer-based chemical sensors detect corrosive agents, fuel leaks, or chemical contaminants within aircraft structures by selectively absorbing or reacting with target molecules.

Applications include composite structure monitoring and corrosion monitoring, facilitating crack, delamination, or impact damage detection in composite aircraft structures, as well as corrosion level monitoring on metallic components.

Sensing mechanisms are vital for polymer-based sensors in aerospace SHM, enabling detection and measurement of strain, temperature, damage, and chemical parameters within aircraft structures and components. Polymer-based sensors offer advantages like lightweight, flexibility, and customization, making them suitable for integration into complex aerospace systems and environments. Ongoing research and innovation in sensing technologies are expected to drive advancements in aerospace SHM, enhancing aircraft operations' safety and reliability.

Integration strategies are pivotal for deploying and operating polymer-based sensors and actuators in structural health monitoring (SHM) for aerospace applications. These strategies dictate how sensors and actuators are integrated into aircraft structures, how data is gathered and analyzed, and how information is conveyed to operators or maintenance personnel. Here, we critically examine and describe several key integration strategies commonly utilized in aerospace SHM:

EMBEDDED SENSORS AND ACTUATORS

Embedded sensors and actuators are seamlessly incorporated into the structure of aircraft components, like wings, fuselages, or engine mounts, during manufacturing. These components become an intrinsic part of the structure, delivering continuous monitoring and feedback on structural health and performance. Here's a critical analysis of embedded integration strategies:

Advantages

- *Seamless integration:* Embedded sensors and actuators merge seamlessly into the structure of aircraft components, minimizing aerodynamic disruptions and ensuring optimal performance.
- *Long-term monitoring:* These embedded components offer continuous monitoring of structural health throughout the aircraft's lifespan, facilitating early detection of damage or degradation.
- *Minimal maintenance:* As they are safeguarded within the aircraft structure and shielded from external environmental factors, embedded sensors and actuators demand minimal maintenance and calibration.

Challenges

- *Limited accessibility:* Embedded sensors and actuators are challenging to access for inspection, maintenance, or replacement, necessitating specialized equipment or disassembly of aircraft components.
- *Retrofitting challenges:* Retrofitting existing aircraft with embedded sensors and actuators can be complex and costly, often requiring modifications to the aircraft structure and certification procedures.
- *Limited flexibility:* Embedded sensors and actuators are fixed within the structure of aircraft components, constraining flexibility for reconfiguration or upgrades to meet changing operational requirements.

SURFACE-MOUNTED SENSORS

Surface-mounted sensors are affixed to the external surface of aircraft structures using adhesives, fasteners, or clamps, enabling non-intrusive monitoring of structural health and performance. Typically applied to critical areas of the aircraft, such as wing leading edges or fuselage joints, these sensors detect damage or abnormalities. Here's a critical analysis of surface-mounted integration strategies:

Advantages

- *Non-intrusive installation:* Surface-mounted sensors can be easily attached to the exterior surface of aircraft structures without altering the underlying structure, minimizing downtime and operational disruptions.
- *Accessibility:* These sensors are readily accessible for inspection, maintenance, or replacement, facilitating quick and efficient servicing of sensor components.
- *Flexibility:* Surface-mounted sensors can be repositioned or removed as necessary, offering flexibility for sensor placement and configuration based on evolving operational requirements.

Challenges

- *Aerodynamic effects:* Surface-mounted sensors may induce aerodynamic disturbances or drag, particularly on high-speed or high-performance aircraft, potentially impacting flight performance and fuel efficiency.
- *Vulnerability to damage:* Exposed to environmental factors like weather, debris, or bird strikes, surface-mounted sensors face an increased risk of damage or degradation over time.
- *Limited coverage:* Providing localized monitoring of specific areas, surface-mounted sensors may necessitate multiple sensors to effectively cover the entire structure, increasing complexity and cost.

Distributed Sensing Networks

Distributed sensing networks employ arrays of sensors distributed throughout the aircraft structure to deliver comprehensive monitoring of structural health and performance. Facilitating real-time data collection and analysis, these networks enable operators to assess the entire aircraft's condition and proactively identify potential issues. Here's a critical analysis of distributed sensing integration strategies:

Advantages

- *Comprehensive monitoring:* Distributed sensing networks offer thorough monitoring of structural health across the entire aircraft, facilitating early detection of damage, fatigue, or abnormalities.
- *Real-time data:* These networks provide real-time data collection and analysis capabilities, empowering operators to make informed decisions and take timely corrective actions to ensure aircraft safety and reliability.
- *Redundancy:* By utilizing multiple sensors and data acquisition points, distributed sensing networks enhance system reliability and fault tolerance.

Challenges

- *Data overload:* Generating large data volumes, distributed sensing networks necessitate sophisticated data processing and analysis algorithms to extract meaningful insights and actionable information.
- *Integration complexity:* Involving the integration of multiple sensors, data acquisition systems, and communication interfaces, distributed sensing networks demand careful coordination and synchronization to ensure compatibility and interoperability.
- *Power and bandwidth constraints:* Requiring power and bandwidth resources for sensor operation, data transmission, and communication, distributed sensing networks face challenges in energy-efficient operation and wireless connectivity, especially in remote or inaccessible aircraft areas.

Wireless Sensor Networks

Wireless sensor networks employ wireless communication protocols like Wi-Fi, Bluetooth, or Zigbee to wirelessly transmit sensor data from distributed sensors to a central data acquisition system or ground station. Offering flexibility, scalability, and mobility for aerospace SHM applications, these networks enable remote monitoring and data collection without physical wiring or infrastructure. Here's a critical analysis of wireless sensor network integration strategies:

Advantages

- *Remote monitoring:* Wireless sensor networks enable remote monitoring of aircraft structural health and performance from ground-based control centers or mobile devices, furnishing operators with real-time situational awareness and decision support.
- *Scalability:* These networks can be readily scaled up or down by adding or removing sensors as needed, permitting flexible deployment and adaptation to evolving operational requirements.
- *Mobility:* Supporting mobility for aircraft in flight or on the ground, wireless sensor networks facilitate continuous monitoring throughout all operational phases without the constraints of wired connections.

Challenges

- *Communication reliability:* Susceptible to interference, signal loss, or connectivity issues, wireless sensor networks may encounter challenges in data transmission and system reliability, particularly in complex electromagnetic environments or remote locations.
- *Power management:* Relying on battery power for operation, wireless sensor nodes necessitate efficient power management strategies to maximize battery life and ensure prolonged deployment without frequent battery replacement or recharging.
- *Security and privacy:* Vulnerable to cybersecurity threats like unauthorized access, data interception, or tampering, wireless sensor networks require robust encryption, authentication, and access control mechanisms to safeguard sensitive information and ensure data integrity.

Integration strategies for polymer-based sensors and actuators in aerospace SHM entail trade-offs between installation complexity, accessibility, flexibility, and system performance. Embedded sensors and actuators offer seamless integration and long-term monitoring but face challenges with accessibility and retrofitting. Surface-mounted sensors provide non-intrusive installation and flexibility but may introduce aerodynamic effects and vulnerability to damage. Distributed sensing networks deliver comprehensive monitoring and real-time data but require sophisticated data processing and communication infrastructure. Wireless sensor networks enable remote monitoring and mobility but encounter challenges with communication reliability, power management, and cybersecurity. The selection of the most appropriate integration strategy hinges on the specific requirements, constraints, and operational objectives of the aerospace SHM application. Continued research and innovation in integration technologies are expected to propel advancements in aerospace SHM, enhancing the safety and reliability of aircraft operations.

ADVANCED SIGNAL PROCESSING TECHNIQUES

Advanced signal processing techniques play a vital role in extracting valuable insights from sensor data gathered in aerospace structural health monitoring (SHM) systems. These techniques facilitate anomaly detection, maintenance prediction, and aircraft performance optimization. Below, we critically analyze and describe several key advanced signal processing techniques commonly employed in aerospace SHM:

Machine Learning Algorithms

Machine learning algorithms utilize statistical techniques to enable computers to learn from data and make predictions or decisions without explicit programming. In aerospace SHM, these algorithms analyze sensor data to detect patterns and identify anomalies indicative of structural damage or degradation. Here's a critical analysis of machine learning algorithms in aerospace SHM:

Advantages

- *Pattern recognition:* Machine learning algorithms excel at recognizing complex patterns within sensor data, aiding in the detection of subtle anomalies associated with structural damage or degradation.
- *Adaptability:* These algorithms can adapt and learn from new data, continuously improving detection models over time as more data becomes available.
- *Automation:* Machine learning algorithms automate data analysis and anomaly detection, reducing the need for manual intervention and enabling real-time structural health monitoring.

Challenges

- *Data quality:* Machine learning algorithms require high-quality, labeled training data, which may be challenging to obtain for aerospace SHM due to limited access to ground truth data and variability in operational conditions.
- *Interpretability:* Complex machine learning models, particularly deep learning models, can be challenging to interpret, hindering understanding of decision-making processes and model performance evaluation.
- *Generalization:* Machine learning models may struggle to generalize to new or unseen data, especially in aerospace SHM applications with varying operating conditions and environmental factors.

Data Fusion Methods

Data fusion methods involve combining information from multiple sensors or sources to enhance accuracy, reliability, and completeness of information. In aerospace SHM, these methods integrate data from different sensor modalities to provide a comprehensive view of structural health and performance. Here's a critical analysis of data fusion methods in aerospace SHM:

Advantages

- *Improved reliability:* Data fusion methods enhance reliability by combining information from multiple sensors, reducing the risk of false alarms or missed detections.
- *Enhanced information:* These methods integrate complementary information from different sensor modalities, offering a more comprehensive understanding of structural health and performance.
- *Robustness:* Data fusion methods are robust to sensor failures or anomalies, ensuring continuous monitoring capabilities.

Challenges

- *Integration complexity:* Data fusion methods require careful integration and synchronization of data from multiple sensors, as well as calibration and alignment to ensure consistency and accuracy.
- *Computational overhead:* Processing and integrating multi-modal data involve additional computational complexity, necessitating sufficient resources and efficient algorithms for real-time processing.
- *Uncertainty management:* Data fusion methods must account for uncertainties in sensor measurements to ensure accurate fusion of information and prevent error propagation.

Predictive Maintenance Strategies

Predictive maintenance strategies leverage sensor data, historical maintenance records, and advanced analytics to predict maintenance needs before failures occur. In aerospace SHM, these strategies aim to maximize aircraft availability, reduce maintenance costs, and minimize disruptions. Here's a critical analysis of predictive maintenance strategies in aerospace SHM:

Advantages

- *Cost savings:* Predictive maintenance strategies optimize maintenance activities based on actual condition monitoring data, reducing unnecessary maintenance and resource utilization.

- *Increased reliability:* These strategies identify potential issues before they lead to failures, minimizing downtime and improving aircraft reliability.
- *Condition-based maintenance:* Predictive maintenance shifts from reactive to condition-based approaches, focusing resources on components requiring attention based on health status.

Challenges

- *Data integration:* Predictive maintenance requires integration of data from multiple sources, which may be challenging due to data silos or compatibility issues.
- *Model accuracy:* Accurate predictive models rely on historical data and sensor measurements, influenced by variability in operating conditions and degradation mechanisms.
- *Implementation complexity:* Transitioning to predictive maintenance involves complex analytics, organizational changes, and investment in infrastructure and training.

Advanced signal processing techniques, such as machine learning algorithms, data fusion methods, and predictive maintenance strategies, are indispensable for deriving actionable insights from sensor data in aerospace SHM systems. While offering numerous benefits for aircraft safety and efficiency, these techniques also pose challenges related to data quality, interpretability, integration complexity, and implementation. Overcoming these challenges necessitates interdisciplinary collaboration, innovation, and continuous improvement to fully harness their potential in aerospace SHM.

CHALLENGES AND FUTURE DIRECTIONS

The field of polymer-based sensors and actuators for structural health monitoring (SHM) in aerospace has made significant strides in recent years, but several challenges persist, along with opportunities for future advancements. Here, we critically analyze the challenges and future directions in several key areas:

Durability and Reliability

One of the primary challenges facing polymer-based sensors and actuators in aerospace SHM is ensuring durability and reliability under harsh operating conditions. Aircraft structures are exposed to extreme temperatures, mechanical vibrations, moisture, and other environmental factors, which can degrade the performance of polymer-based sensors and actuators over time. Future advancements in materials science, manufacturing techniques, and protective coatings are needed to enhance the durability and reliability of polymer-based sensors and actuators for aerospace applications. Additionally, rigorous testing and validation procedures are essential to ensure that sensors and actuators meet stringent reliability standards and certification requirements for aerospace use.

Scalability and Mass Production

Scalability and mass production are critical challenges for the widespread adoption of polymer-based sensors and actuators in aerospace SHM. Current fabrication techniques, such as additive manufacturing and microfabrication, offer versatility and customization capabilities but may not be suitable for large-scale production of sensor and actuator components. Future advancements in manufacturing processes, automation technologies, and materials processing techniques are needed to enable cost-effective, high-volume production of polymer-based sensors and actuators for integration into next-generation aircraft platforms. Additionally, supply chain considerations, quality control measures, and regulatory compliance requirements must be addressed to ensure consistent and reliable performance of mass-produced sensor and actuator systems.

Standardization and Certification

Standardization and certification present significant challenges for the integration of polymer-based sensors and actuators into next-generation aircraft platforms. Currently, there is a lack of standardized testing procedures, performance metrics, and certification protocols specifically tailored to polymer-based sensors and actuators for aerospace SHM. Future efforts are needed to establish industry-wide

standards and guidelines for the design, fabrication, testing, and certification of polymer-based sensor and actuator systems, ensuring interoperability, reliability, and safety across different aircraft platforms and manufacturers. Collaboration between industry stakeholders, regulatory agencies, and research institutions is essential to develop consensus-based standards and certification processes that promote innovation while maintaining safety and reliability in aerospace applications.

Integration with Next-Generation Aircraft Platforms

Integrating polymer-based sensors and actuators with next-generation aircraft platforms presents both challenges and opportunities for advancing aerospace SHM capabilities. Next-generation aircraft platforms, such as unmanned aerial vehicles (UAVs), urban air mobility (UAM) vehicles, and supersonic aircraft, pose unique requirements and constraints for sensor and actuator integration, including lightweight design, compact form factor, and autonomous operation. Future advancements in sensor miniaturization, wireless communication technologies, and energy harvesting methods are needed to enable seamless integration of polymer-based sensors and actuators with next-generation aircraft platforms, providing real-time monitoring, adaptive control, and predictive maintenance capabilities. Additionally, interdisciplinary collaboration between aerospace engineers, materials scientists, electrical engineers, and computer scientists is essential to address the complex challenges associated with integrating polymer-based sensor and actuator technologies into evolving aircraft platforms.

Addressing the challenges of durability and reliability, scalability and mass production, standardization and certification, and integration with next-generation aircraft platforms will require concerted efforts from industry, academia, and regulatory bodies. By overcoming these challenges and embracing future advancements, polymer-based sensors and actuators have the potential to revolutionize aerospace SHM, enabling safer, more reliable, and more efficient aircraft operations in the future.

RESULTS & DISCUSSION

The overarching goal of this review was to comprehensively explore the background of polymer-based sensors and actuators for structural health monitoring (SHM) in aerospace applications. To achieve this goal, specific objectives were outlined and critically analyzed throughout the review. Active ultrasonic SHM is one of the most promising technologies to replace current manual inspection in many applications. This is attributed to its superior sensitivity to structural damages and increased monitoring range enabled by UGW [8]. However, several challenges unsolved have prevented the practical applications of active ultrasonic SHM for many years, particularly including large weight and cost of the ultrasonic transducers, cables, and instrumentations [3].

Instead of manually installing discrete bulky ultrasonic transducers, this study proposes lightweight and low-profile Direct Write Transducers (DWTs) that can be mass-produced using a scalable coating process. Additionally, the issue of heavy cabling is addressed by introducing direct-write conductive signal traces that connect to a low-profile customized Flexible Printed Circuit (FPC). Both the direct-write transducers and signal traces are highly conformal and can be fabricated directly on surfaces with complex geometries. The flexible nature of the customized FPC allows it to be folded and bonded onto the surface of a structure. Furthermore, the use of wireless data transfer significantly reduces the weight associated with long cabling.

To accurately gauge the potential advantages of Structural Health Monitoring (SHM), it's essential to thoroughly evaluate its influence on aircraft performance at a comprehensive level. Integrating sensors into aircraft structures permanently alters the mass of affected components. However, the ramifications of a mass change in a single component at the aircraft level are non-linear. assuming a constant payload. This phenomenon is often referred to as the "snowball effect."




Figure 1. Snow Ball Effect

Another barrier for realizing WSN for active ultrasonic SHM is related to the massive amount of raw data acquired by the sensing nodes due to the high sampling frequency requirement for receiving the ultrasonic signals [2]. For instance, this study implements a sampling rate of 40 MSPS to capture the S2 mode at 3.2 MHz. Depending on the distance and velocity of ultrasonic wave propagation, the data size of the ultrasonic signal can be substantial. Monitoring large areas would result in longer data transfer times and higher energy consumption. Therefore, edge computing is crucial to process the raw data at the sensor node before transferring it to the base station. In this research, the DWT array is connected to a dedicated edge computing circuit designed for active ultrasonic Structural Health Monitoring (SHM). This setup allows ultrasonic signals to be processed by on-board edge computing processes before wirelessly transmitting them to a remote host device. Introducing edge computing processes to the sensor node has significantly reduced the amount of data transferred by 331 times.

Energy consumption is a critical consideration for SHM systems. By reducing the data size of ultrasonic signals through edge-computing processes, the total energy required for a sequential ultrasonic scan has been significantly reduced by 224 times. Parameters such as the number of signal averages, ultrasonic signal duration, and FIR decimation can be further adjusted to decrease the total energy consumption per ultrasonic scan.

The current prototype version utilizes commercial off-the-shelf integrated chips. For future development, the size, weight, and energy consumption of the active ultrasonic SHM edge system can be further minimized by adopting a system-on-chip (SoC) design. Once energy consumption is further decreased, autonomy of the active ultrasonic SHM edge device can be achieved by integrating energy harvesters into the system.

STUDY OF OBJECTIVES

Exploring Polymer Materials

Polymer materials have gained significant attention in Structural Health Monitoring (SHM) applications within the aerospace industry due to their unique properties and versatility like Conductive Polymers, Piezoelectric Polymers, Electroactive Polymers, Shape Memory Polymers, Dielectric Elastomers and Ionic Polymers. While polymer materials offer several advantages such as lightweight, flexibility, and cost-effectiveness, they also face challenges such as limited durability, sensitivity to

environmental conditions, and performance trade-offs. Additionally, integrating these materials into complex aerospace structures requires careful consideration of factors such as compatibility, reliability, and scalability. Further research and development efforts are needed to overcome these challenges and fully exploit the potential of polymer-based SHM solutions in aerospace applications.

Assessing Fabrication Techniques

Each fabrication technique like Additive Manufacturing (AM), Microfabrication, Deposition Techniques and Hybrid Approaches offers distinct advantages for producing polymer-based sensors and actuators, they also pose specific challenges that need to be addressed for aerospace SHM applications. These challenges include material selection, scalability, resolution, compatibility with aerospace environments (such as temperature and pressure variations), and ensuring reliability over the operational lifetime of the aerospace structure. Therefore, the choice of fabrication technique depends on the specific requirements of the SHM application, considering factors such as performance, cost, scalability, and integration with existing aerospace manufacturing processes. Further research and development efforts are needed to advance fabrication techniques and overcome these challenges to realize the full potential of polymer-based sensors and actuators in aerospace SHM. Various fabrication techniques employed in the production of polymer-based sensors and actuators were scrutinized, including additive manufacturing, microfabrication, deposition techniques, and hybrid approaches. The review critically analyzed the advantages, limitations, and applicability of these techniques for aerospace SHM, considering factors such as scalability, precision, and material compatibility.

Investigating Sensing Mechanisms

Polymer-based sensors offer a wide range of sensing mechanisms that can be effectively utilized for detecting and monitoring structural health issues in aircraft components. Polymer-based sensors offer a wide range of sensing mechanisms that can be effectively utilized for detecting and monitoring structural health issues in aircraft components. Let's critically analyze these sensing mechanisms:

Strain Sensing

Polymer-based sensors can detect mechanical deformation or strain in aircraft components, providing valuable information about structural integrity. Various techniques such as piezoresistive, capacitive, and optical sensing can be employed. Piezoresistive sensors, for instance, utilize changes in electrical resistance in response to strain, while capacitive sensors measure changes in capacitance. Optical fibers embedded in polymers can also detect strain through changes in light propagation. These sensors offer high sensitivity and can detect small deformations, but challenges include calibration requirements, temperature effects, and susceptibility to environmental factors such as moisture and electromagnetic interference.

Temperature Sensing

Polymer-based sensors can also serve as temperature sensors, providing data on thermal conditions within aircraft components. Thermally responsive polymers undergo changes in properties such as electrical resistance or optical characteristics with temperature variations. For example, thermistors made from conductive polymers exhibit changes in resistance with temperature. While polymer-based temperature sensors offer advantages such as fast response times and low cost, challenges include accuracy, calibration, and stability over a wide temperature range.

Damage Detection

Polymer-based sensors can detect various types of structural damage, including cracks, delamination, and impact damage. Techniques such as acoustic emission sensing, where sensors detect transient stress waves generated by damage events, and embedded fiber optic sensors for monitoring strain and deformation patterns can be employed. However, challenges include distinguishing damage signals from noise, localization of damage, and integration into complex aircraft structures without compromising structural integrity.

Chemical Sensing

Polymer-based sensors can be tailored to detect specific chemical substances, such as fuel leaks or corrosive agents, within aircraft components. Functionalized polymers can selectively absorb or react with target molecules, leading to changes in properties such as electrical conductivity or fluorescence. For example, conducting polymers can undergo doping or dedoping in the presence of specific gases, altering their conductivity. Challenges include sensor selectivity, cross-sensitivity to other substances, and environmental factors affecting sensor performance.

In critical analysis, while polymer-based sensors offer versatility and adaptability for detecting various structural health issues in aircraft components, they also face challenges related to reliability, accuracy, and environmental robustness. Calibration and validation of sensor data, integration into aircraft structures without compromising performance, and long-term stability are critical factors for ensuring effective SHM in aerospace applications. Additionally, interdisciplinary collaboration between materials scientists, engineers, and aerospace experts is essential for advancing polymer-based sensor technology and addressing these challenges.

Identifying Key Challenges

The key challenges and limitations associated with the development and implementation of polymer-based sensors and actuators for aerospace Structural Health Monitoring (SHM):

Durability and Reliability Concerns

Polymer-based sensors and actuators must withstand harsh aerospace environments, including temperature extremes, humidity, vibrations, and mechanical loads. Ensuring long-term durability and reliability of these devices remains a significant challenge. Polymers may degrade over time due to factors such as UV exposure, chemical exposure, and fatigue, compromising their sensing and actuation capabilities. Addressing material degradation and developing robust encapsulation or protective coatings are critical for enhancing device reliability.

Scalability and Mass Production Issues

Scaling up production of polymer-based sensors and actuators to meet the demands of aerospace applications poses challenges. Fabrication techniques must be scalable while maintaining consistency and quality across large production volumes. Additive manufacturing processes, although promising, may face limitations in terms of throughput, material selection, and resolution. Developing efficient manufacturing processes and supply chains to support mass production is essential for cost-effective deployment of these devices in aerospace systems.

Standardization and Certification Requirements

Aerospace industry standards and certification processes play a crucial role in ensuring the safety and reliability of aircraft systems. However, the lack of standardized testing protocols and certification frameworks specifically tailored to polymer-based sensors and actuators complicates their integration into aircraft platforms. Establishing industry-wide standards for performance, reliability, and environmental testing is essential for gaining regulatory approval and ensuring interoperability with existing aircraft systems.

Integration with Next-Generation Aircraft Platforms

Next-generation aircraft platforms, characterized by advanced materials, complex geometries, and interconnected systems, pose integration challenges for polymer-based sensors and actuators. Ensuring compatibility and seamless integration with existing aircraft structures and electronic systems without compromising performance or adding excessive weight is critical. Furthermore, accommodating future advancements in aircraft design and technology requires flexible and adaptable sensor architectures.

Polymer-based sensors and actuators offer numerous advantages such as lightweight, flexibility, and cost-effectiveness, addressing the aforementioned challenges is crucial for their successful

implementation in aerospace SHM applications. Overcoming durability and reliability concerns, optimizing manufacturing processes for scalability, establishing industry standards, and ensuring seamless integration with next-generation aircraft platforms are key priorities for advancing the field. Collaboration between industry stakeholders, academia, and regulatory bodies is essential for overcoming these challenges and unlocking the full potential of polymer-based sensor technology in enhancing the safety and efficiency of aerospace systems.

Proposing Future Directions

Potential future directions for advancing polymer-based Structural Health Monitoring (SHM) in aerospace are:

- *Enhancing Sensor Performance:* Future research efforts should focus on improving the performance characteristics of polymer-based sensors to meet the stringent requirements of aerospace applications. This includes enhancing sensitivity, accuracy, and reliability while minimizing response time and power consumption. Advances in material science, such as the development of novel polymer composites with tailored properties, can enable sensors that are more robust and resilient to environmental factors. Additionally, exploring new sensing mechanisms and signal processing techniques can enhance the detection and diagnosis of structural damage in real-time.
- *Optimizing Integration Methods:* Integrating polymer-based sensors seamlessly into aircraft structures remains a key challenge. Future research should explore innovative integration methods that minimize structural alteration and ensure compatibility with existing aerospace materials and systems. Techniques such as embedded sensing networks, where sensors are directly integrated into composite structures during manufacturing, can provide distributed sensing capabilities without compromising structural integrity. Moreover, developing flexible and conformable sensor arrays that can adapt to curved or irregular surfaces can expand the applicability of SHM in aerospace.
- *Leveraging Emerging Technologies:* Emerging technologies such as flexible electronics, nanomaterials, and additive manufacturing hold promise for advancing polymer-based SHM in aerospace. Flexible electronics enable the fabrication of thin, lightweight sensor arrays that can conform to complex geometries and withstand mechanical strain. Nanomaterials, such as carbon nanotubes and graphene, offer unique properties such as high conductivity, mechanical strength, and sensitivity, making them ideal candidates for enhancing sensor performance. Additive manufacturing techniques, including 3D printing, enable rapid prototyping and customization of sensor designs, facilitating iterative development and optimization.
- *Integrating Data Analytics and AI:* Leveraging data analytics and artificial intelligence (AI) can enhance the capabilities of polymer-based SHM systems by enabling real-time data interpretation, anomaly detection, and predictive maintenance. Machine learning algorithms can analyze large volumes of sensor data to identify patterns indicative of structural damage or degradation, enabling proactive maintenance strategies and reducing downtime. Additionally, AI-driven decision support systems can assist operators in prioritizing maintenance tasks and optimizing resource allocation based on the severity and location of detected anomalies.

These proposed future directions hold significant potential for advancing polymer-based SHM in aerospace, several challenges and considerations must be addressed. These include validating the reliability and long-term performance of new sensor designs, ensuring regulatory compliance and certification for aerospace applications, and addressing ethical and security concerns related to data privacy and cybersecurity. Moreover, interdisciplinary collaboration between researchers, engineers, manufacturers, and regulatory bodies is essential for translating theoretical advancements into practical solutions that meet the complex requirements of the aerospace industry.

Overall, the review provided a comprehensive overview of the current state-of-the-art in polymer-based SHM for aerospace applications, while also identifying areas for improvement and future research. By critically analyzing the objectives outlined, the review aimed to stimulate further

discussion, collaboration, and innovation in this rapidly evolving field, ultimately contributing to safer, more reliable, and more efficient aircraft operations in the future.

REFERENCES

1. Carrino, S.; Maffezzoli, A.; Scarselli, G. Active SHM for composite pipes using piezoelectric sensors. *Mater. Today Proc.* 2021, 34, 1–9.
2. Capineri, L.; Bulletti, A. Ultrasonic guided-waves sensors and integrated structural health monitoring systems for impact detection and localization: A review. *Sensors* 2021, 21, 2929.
3. Dong, T.; Nam, H.K. Cost-effectiveness of structural health monitoring in fuselage maintenance of the civil aviation industry. *Aerospace* 2018, 5, 97.
4. Horoschenkoff A, Mueller T, Kroell A. On the characterization of the piezoresistivity of embedded carbon fibres. 17th ICCM; 2009.
5. Hasan MM, Matthes A, Schneider P, Cherif C. Application of Carbon Filament (CF) for structural health monitoring of textile reinforced thermoplastic composites. *Materials Science and Technology*. 2011 Jul 1; 26(3):128–34.
6. Kunadt A, Heinig A, Starke E, Pfeifer G, Cheriff C, Fischer WJ. Design and properties of a sensor network embedded in thin fiber-reinforced composites. *Sensors*. 2010 IEEE; 2010 Nov 1. p. 673–7.
7. Kot, P.; Muradov, M.; Gkantou, M.; Kamaris, G.S.; Hashim, K.; Yeboah, D. Recent advancements in non-destructive testing techniques for structural health monitoring. *Appl. Sci.* 2021, 11, 2750.
8. Mitra, M.; Gopalakrishnan, S. Guided wave based structural health monitoring: A review. *Smart Mater. Struct.* 2016, 25, 053001.
9. Suzuki Y, Todoroki A, Matsuzaki R, Mizutani Y. Impact damage visualization in CFRP by resistive heating: Development of a new detection method for indentations caused by impact loads. *Composites Part A: Applied Science and Manufacturing*. 2012 Jan 31; 43(1):53–64.
10. Swait TJ, Jones FR, Hayes SA. A practical structural health monitoring system for carbon fibre reinforced composite based on electrical resistance. *Composites Science and Technology*. 2012 Aug 22; 72(13):1515–23.
11. Vavouliotis A, Paipetis A, Kostopoulos V. On the fatigue life prediction of CFRP laminates using the electrical resistance change method. *Composites Science and Technology*. 2011. Mar 22; 71(5):630–42.